



TSE Industries, Inc.
4370 112th Terrace North
Clearwater, FL 33762 (USA)
727-573-7676 or 800-237-7634 www.tse-industries.com

Formula ID 1676 Compound XP-5798-F Cure: P Color: B
Urethane Type: Polyether

Application: 72 Shore A Black Millathane® 97 Molding Compound

Millathane® 97	100.00	Durometer, Shore A	72	
Stearic Acid	0.25	Durometer, Shore D		
N330 Black	20.00	25% Modulus, psi		MPa
Ultrasil VN3	20.00	50% Modulus, psi		MPa
Silquest A-172	0.40	100% Modulus, psi	335	2.3 MPa
DBEEA (TP-95)	5.00	200% Modulus, psi	735	5.1 MPa
Struktol WB-222	0.50	300% Modulus, psi	1280	8.8 MPa
Irganox 1010	0.25	Tensile Strength, psi	2890	19.9 MPa
SR 231 (DEGDMA)	3.00	Elongation, %	550	
SR 350 (TMPTMA/TRIM)	2.00	Tear Die C, lb/in.	191	33.4 kN/m
DiCup 40C	1.50	Tear Die B, lb/in.	325	56.9 kN/m
		Specific Gravity, g/cc	1.170	
		CureTime, minutes	7	
		Cure Temp°F	320	160 °C
		Mooney Viscosity, ML4/100°C	53	
		Heat Aging <input type="text"/> Hrs at <input type="text"/> °C		
		Hardness Change, pts.		
		Tensile Change, %		
		Elongation Change, %		
		Fluid Aging <input type="text"/> Hrs at <input type="text"/> °C		
		Hardness Change, pts.		
		Tensile Change, %		
		Elongation Change, %		
		Volume Change, %		
		Surface Resistivity, ohm/cm ²		
		Volume Resistivity, ohm-cm		
		UL 94 Rating:		
	Total		152.90	
	Brittle Point, °C			
	TR10, °C (ASTM D1329)			
	Bashore Resilience, %		48	
	DIN Abrasion, mm ³ loss		91	
	Compression Set 22h/70°C, %		23	
	Compression Set 70h/70°C, %			
	Compression Set 22h/100°C, %			
	Compression Set 70h/100°C, %			
	Compression Set 22h/125°C, %			
	Compression Set 22h/150°C, %			
	Compression Set, Other conditions:			
	<input type="text"/> h/ <input type="text"/> °C, %			

Other Tests and Info: MDR at 160°C: t90=7.0 min.

3/25/2010

The recommendations for the use of our products are based on tests believed to be reliable. However, we do not guarantee the results to be obtained by others under different conditions. Nothing in this literature is intended as a recommendation to use our products so as to infringe on any patent. Millstab™ is a trademark, and Millathane® and Thanecure® are registered trademarks of TSE Industries, Inc.