



TSE Industries, Inc.
 4370 112th Terrace North
 Clearwater, FL 33762 (USA)
 727-573-7676 or 800-237-7634 www.tse-industries.com

Formula ID 2303 Compound XP-8219-B Cure: P Color: NB

Urethane Type: Polyester

Application: 90 Shore A Non-Black, Peroxide-Cured Millathane® HT Premilled Compound

Millathane® HT Premilled	101.50	Durometer, Shore A	90	
Stearic Acid	0.30	Durometer, Shore D		
Wacker HDK-N20 fumed silica	35.00	Durometer, Asker C		
Silquest RC-1	0.70	25% Modulus, psi		MPa
DBEEA (TP-95)	5.00	50% Modulus, psi		MPa
Struktol WB-222	0.50	100% Modulus, psi	1635	11.3 MPa
SR 517	5.00	200% Modulus, psi	3000	20.7 MPa
SR 231 (DEGDMA)	3.00	300% Modulus, psi		MPa
DiCup 40C	1.25	Tensile Strength, psi	3065	21.1 MPa
		Elongation, %	205	
		Tear Die C, lb/in.	168	29.4 kN/m
		Tear Die B, lb/in.	296	51.8 kN/m
		Tear Die T, lb/in.		kN/m
		Specific Gravity, g/cc	1.324	
		CureTime, minutes	15	
		Cure Temp°F	320	160 °C
		Mooney Viscosity, ML4/100°C		
		Heat Aging 24 Hrs at 150 °C		
		Hardness Change, pts.	2	
		Tensile Change, %	10	
		Elongation Change, %	-22	
		Fluid Aging Oil, IRM 903		
		24 Hrs at 70 °C		
		Hardness Change, pts.	1	
		Tensile Change, %	4	
		Elongation Change, %	0	
		Volume Change, %	0.2	
		Surface Resistivity, ohm/cm ²		
		Volume Resistivity, ohm-cm		
		UL 94 Rating:		
Total	152.25			
Brittle Point, °C				
TR10, °C (ASTM D1329)				
Bashore Resilience, %	29			
DIN Abrasion, mm ³ loss	143			
Compression Set 22h/70°C, %	19			
Compression Set 70h/70°C, %				
Compression Set 22h/100°C, %				
Compression Set 70h/100°C, %				
Compression Set 22h/125°C, %				
Compression Set 22h/150°C, %				
Compression Set, Other conditions:				
	h/ °C, %			

Other Tests and Info:

7/24/2017

The recommendations for the use of our products are based on tests believed to be reliable. However, we do not guarantee the results to be obtained by others under different conditions nor do we guarantee that this or other formulas will work in a specific application . Nothing in this literature is intended as a recommendation to use our products so as to infringe on any patent. Millstab™ is a trademark, and Millathane® and Thanecure® are registered trademarks of TSE Industries, Inc. All other brand names and product names referenced are trademarks, registered trademarks or trade names of their respective holders.