



Product information

Duro-Glide[®] # 912 Dry Glide

Duro-Glide[®] – #912 Dry Glide is a superior UHMW Polymer with a molecular weight of 7 – 9 million This special formula was designed for the packaging and machine industry. Excellent for use in dry run conveyor applications. The anti-static filler additive also reduces static build up on fast moving equipment.

Properties: reduced coefficient of friction
 UV-stabilized
 Antistatic reduced
 noise level reduction

Color: Black # 912

Application fields: conveying and packaging industry
 package delivery industry
 canning industry
 material handling

TSE-OK, L.L.C.

4370 112th Terrace North, Clearwater, Florida 33762
866-652-2557 / Fax 727-456-2899
WWW.TSE-OK.COM / E-Mail: SALES@TSE-OK.COM

Physical Properties Data Sheet

Duro-Glide[®] # 912 Dry Glide (UHMW – PE) Characteristics and standard values

Physical Properties	Method	SI Unit	SI Value
Density	ASTM D792 ISO 1183-1	g/cc g/cm ³	> 0.93 > 0.93
Abrasion (Sand-Slurry-Test rel. to GUR 4120 = 100%)	ISO 15527	% (Average)	75 - 80
Notched impact strength	ISO 11542-2	mJ/mm ² kJ/m ²	> 100
Tensile strength, yield	ASTM D638 ISO 527-2	psi MPa	> 2500 > 17
Break elongation	ASTM D638 ISO 527-2	% %	> 250 > 50
Creep properties under varying compressive stress : Creep <10%	max.	psi MPa	1450 10
Coefficient of friction, ASTM 1894 metal= Rz 2,5 μ, Pm= 2 N/mm ² , V= 150 mm/min	Static Dynamic	μ μ	0.15 0.09
Shore-hardness, 3-s-value 6mm plate	ASTM D2240 ISO 868 / DIN 53505	D D	62 62
Water absorption	---	%	< 0.1 (Nil)
Flammability	UL 94	---	HB
Thermal Properties			
Melt temperature	ASTM 3417 (DSC) ISO 3146 (DSC)	°F °C	275 – 278 135 – 137
Permanent operation temp., max.	---	°F °C	176 80
Coefficient of linear expansion	ASTM D696 DIN 53752	73 – 176 °F 23 – 80°C	≈ 1.1x10 ⁻⁴ /°F ≈ 2.0x10 ⁻⁴ /°C
Electrical Properties			
Surface resistivity	ASTM D257 IEC 93	Ohm Ω	< 10 ⁹ < 10 ⁹
Volume resistivity	ASTM D257 IEC 93	Ohm-cm Ω*cm	< 10 ⁹ < 10 ⁹

Any suggestions or recommendations for the use of our products are based on tests believed to be reliable and on the independent judgment of our technicians. However, it is ultimately up to the Customer/End User to determine whether the product(s) provided by TSE-OK, LLC are suitable for the intended purpose or application. TSE-OK, LLC makes no warranty of fitness for a particular purpose, nor does it guarantee the results to be obtained. Nothing in this literature is intended as a recommendation to use our products so as to infringe on any patent.

TSE-OK, L.L.C.

4370 112th Terrace North, Clearwater, Florida 33762
866-652-2557 / Fax 727-456-2899
WWW.TSE-OK.COM / E-Mail: SALES@TSE-OK.COM