

Technical Information for Performance Solutions

Special points of interest:

- High Hardness Millathane® 97 Compounds
- Color

HIGH HARDNESS MILLATHANE® 97 COMPOUNDS

High hardness (over 85 Shore A) compounds can be made using Millathane 97 and high levels of fillers and/or co-agents. Typically, compounds with high levels of fillers are boardy in the uncured state, with high viscosity, and hence difficult to process. Combining a moderate level of filler with relatively high levels of co-agents can give compounds with improved processing characteristics while retaining the good properties of urethanes. With Millathane 97, compounds prepared with fumed silica as the filler can be transparent or translucent and thus resemble cast urethanes.



MILLATHANE® FACTOID:
*DID YOU KNOW THAT
MILLATHANE® TECHNICAL
REPORTS AND COMPOUND
FORMULAS ARE AVAILABLE ON
OUR WEBSITE? GO TO
WWW.MILLATHANE.COM; THEN,
CLICK THE LINK ON THE RIGHT
FOR "MILLATHANE TECHNICAL
INFO".*

MILLATHANE® FACTOID:
*DID YOU KNOW THAT MILLATHANE 66
CAN BE USED FOR DRY FOOD CONTACT
APPLICATIONS? THIS POLYMER
COMPLIES WITH 21CFR177.1680 FOR
USES THAT INVOLVE DRY FOOD CONTACT
ONLY. MILLATHANE GRADES FOR WET
FOOD CONTACT ARE UNDER
DEVELOPMENT. IF YOU HAVE AN
APPLICATION REQUIRING WET FOOD
CONTACT, PLEASE CONTACT US FOR
FURTHER INFO.*

The table below shows the effect of increasing the fumed silica by 5 parts and the liquid co-agent SR-350 (TMPTMA) by 8 parts. The hardness increased from 83 to 91 Shore A.

	1	2
Millathane® 97	100	100
Wacker HDK N20 (fumed silica)	40	45
TP-95	2	2
AC 617A	2	2
Stearic Acid	0.5	0.5
Carbowax 3350	2.5	2.5
Silquest A-172	2	2
SR 350	12	20
DiCup R	1	1
Irganox 1010	0.25	0.25
Cured hardness, Shore A	83	91

Compound 2, above, is being used commercially to mold small diaphragms and it molds well in spite of its high viscosity (146 Mooney units).

To improve processing of the high hardness compound, lower silica and higher methacrylate levels were investigated. To prevent the compound from getting too highly crosslinked with the trifunctional SR350, which typically yields low elongation and low tear strength, the additional methacrylate used was the difunctional SR-231 (DEGDMA). The data on the following page shows the benefit of these changes to viscosity while keeping the high hardness and good properties.

COLOR

The compounds on the following page will be a clear, with very slight yellowish tint (see picture below). For a “cleaner” transparent color, a small amount (0.005 phr) of ultramarine blue can be added. To make the compound more yellowish, to mimic the look of cast urethanes, a small amount of yellow and/or brown pigment may be used.



	2	3	4
Millathane® 97	100	100	100
Fumed Silica (Wacker HDK N20)	45	35	30
TP-95 (DBEEA)	2	2	2
AC617A Polyethylene	2	2	2
Stearic Acid	0.5	0.5	0.5
Carbowax 3350	2.5	2	2
Silquest A-172	2	1.5	1.5
Irganox 1010	0.25	0.25	0.25
SR-350 (TMPTMA)	20	20	20
SR-231 (DEGDMA)	—	10	20
Dicumyl peroxide	1	1	1
Total	175.25	174.25	179.25
Specific Gravity	1.19	1.15	1.13

Mooney Viscosity, ML(1+4)/100°C	146	52	36
--	-----	----	----

Rheometer (MDR) at 160°C (320°F)

ML, lb-in (dNm)	9.1 (10.3)	1.8 (2.1)	1.3 (1.4)
MH, lb-in (dNm)	65.4 (73.9)	91.5 (103)	92.9 (105)
ts1, min	0.2	0.3	0.3
tc50, min.	0.7	0.6	0.6
tc90, min.	2.5	2.2	1.8

As seen above, the reduction in the fumed silica level plus the addition of the SR-231 coagent has a dramatic effect on the viscosity of the mixed compound. The rheometer data show that these changes increase the cured torque and shorten the cure times (tc90) somewhat.

Physical Properties, Press Cure conditions:

	5'/160°C	4'/149°C	4'/149°C
Hardness, Shore A	91	94	95
100% Modulus, psi (MPa)	940 (6.5)	1750 (12.0)	1990 (13.7)
200% Modulus, psi (MPa)	1740 (12.0)	—	3060 (21.1)
Tensile Strength, psi (MPa)	3070 (21.1)	2450 (16.9)	3300 (22.7)
Elongation, %	315	180	220
Tear, Die C, lb/in (kN/m)	201 (35.2)	164 (28.8)	174 (30.4)
Compression Set, 22 hr/70°C	32	26	21
Resilience, Bashore, %	50	43	43

The cured data above show excellent physical properties with all compounds. Compression set was improved with the higher coagent/lower silica compound while resilience was reduced slightly.

TSE INDUSTRIES

4370 112th Terrace North
Clearwater, FL , USA 33762-4902

Toll Free: 800-237-7634
Phone: 727-573-7676
Fax: 727-572-0487
E-mail: millgumsinfo@tse-industries.com



www.tse-industries.com



Technology / Service /
Experience

An ISO 9001:2000
Certified Company

We are here to serve you:

Tom Jablonowski, <i>Technical Service Manager</i>	tom.jablonowski@tse-industries.com
Jim Ahnemiller, <i>Technical Director</i>	jim.ahnemiller@tse-industries.com
Nina Manee, <i>Sales & Marketing Representative</i>	nina.manee@tse-industries.com
Jerry McCall, <i>Director of Sales & Marketing</i>	jerry.mccall@tse-industries.com