



Formula ID 2222 Compound XP-7561-C Cure: P Color: NB
Urethane Type: Polyether

Application: 65 Shore A, Transparent Millathane® 97 Footwear Compound

Millathane® 97	100.00	Durometer, Shore A	65	
Stearic Acid	0.20	Durometer, Shore D		
Wacker HDK-N20 fumed silica	20.00	Durometer, Asker C		
Silquest A-172	0.40	25% Modulus, psi		MPa
Songnox 1010	0.30	50% Modulus, psi		MPa
Songsorb 3280	0.30	100% Modulus, psi	230	1.6 MPa
Tinuvin 765	0.30	200% Modulus, psi	345	2.4 MPa
SR 231 (DEGDMA)	3.00	300% Modulus, psi	570	3.9 MPa
Luperox 231	0.60	Tensile Strength, psi	3670	25.3 MPa
		Elongation, %	655	
		Tear Die C, lb/in.	195	34.1 kN/m
		Tear Die B, lb/in.	330	57.8 kN/m
		Tear Die T, lb/in.		kN/m
		Specific Gravity, g/cc	1.105	
		CureTime, minutes	3	
		Cure Temp°F	302	150 °C
		Mooney Viscosity, ML4/100°C		
		Heat Aging <input type="text" value="3840"/> Hrs at <input type="text" value="40"/> °C		
		Hardness Change, pts.		
		Tensile Change, %		
		Elongation Change, %		
		Fluid Aging <input type="text"/> Hrs at <input type="text"/> °C		
		Hardness Change, pts.		
		Tensile Change, %		
		Elongation Change, %		
		Volume Change, %		
		Surface Resistivity, ohm/cm ²		
		Volume Resistivity, ohm-cm		
		UL 94 Rating:		
		Total	125.10	
Brittle Point, °C				
TR10, °C (ASTM D1329)				
Bashore Resilience, %				
DIN Abrasion, mm ³ loss	70			
Compression Set 22h/70°C, %				
Compression Set 70h/70°C, %				
Compression Set 22h/100°C, %				
Compression Set 70h/100°C, %				
Compression Set 22h/125°C, %				
Compression Set 22h/150°C, %				
Compression Set, Other conditions:				
	<input type="text"/> h/ <input type="text"/> °C, % <input type="text"/>			

Other Tests and Info: Heat aging is UVCON accelerated UV test, 40°C and UVA-340 bulbs continuous exposure; no crazing or cracking after 3840 hours (160 days) and only slight yellowing. For better yellowing resistance after humidity exposure, replace Songnox 1010/Songsorb 3280/Tinuvin 765 with Songnox 2450/Sabostab UV62/Sabostab UV312

10/1/2020

The recommendations for the use of our products are based on tests believed to be reliable. However, we do not guarantee the results to be obtained by others under different conditions nor do we guarantee that this or other formulas will work in a specific application. Nothing in this literature is intended as a recommendation to use our products so as to infringe on any patent. Millstab™ is a trademark, and Millathane® and Thanecure® are registered trademarks of TSE Industries, Inc. All other brand names and product names referenced are trademarks, registered trademarks or trade names of their respective holders.