

TSE-EZASP™ 9033

Amine-Functional Resin

Product Description

TSE-EZASP™ 9033 is a solvent-free amine functional reactive resin for use with polyisocyanates.

Application

TSE-EZASP 9033 is a low-viscosity amine functional resin for use in the development of high solid polyurethane/polyurea coatings. TSE-EZASP 9033 may be used by itself or blended with hydroxyl-functional acrylic resin and cross-linked with an aliphatic polyisocyanate to create a high solids polyurethane/polyurea clear coat.

TSE-EZASP 9033 can also be mixed with other amine functional resins to obtain different pot life, dry times when making high solids polyurea coatings. It gives the longest pot life of the TSE-EZASP products.

As with any urethane/urea resin, TSE-EZASP 9033 should be tested for any particular application.

Product Specifications

PROPERTY	TYPICAL VALUE
Amine Value	190
Viscosity, cps	1,500
Spec. Gravity	1.07
Weight per gallon, lbs.	8.95

Reactivity

Blend 9033/7981	100	50:50	25:75
Gel Time * min./sec.	6 hours	44 minutes	36 minutes

THE INFORMATION HEREIN IS BELIEVED TO BE CORRECT AND RELIABLE. HOWEVER, NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THESE DATA, AND NONE IS MADE AS TO THE MARKETABILITY OF THE MATERIAL OR ITS FITNESS FOR ANY PURPOSE. THE CONSUMER ACCEPTS THE RESPONSIBILITY OF AND THE CONDITIONS FOR LIABILITY OF USE OF THE PRODUCT.



*With HDI trimer

Storage

TSE-EZASP 9033 must be stored in tightly sealed containers to prevent contact with moisture. Recommended storage temperature range is 32°-140°F (0°-40°C). The shelf life of this material is six months from the date of receipt by the customer, when stored in closed original containers at 76°F (25°C).

Health and Safety Information

The MSDS has been assembled which provides information concerning the health and safety precautions that must be observed when handling TSE-EZASP 9033. Before working with these products, you must read and become familiar with the available information on their hazards, proper use and handling. This cannot be overemphasized.

Product Support:

TSE Industries, Inc.
PU Elastomers Division
5180 113th Avenue North
Clearwater, FL 33760 USA

1-727-573-7676 or 1-800-237-7634

www.tse-industries.com

THE INFORMATION HEREIN IS BELIEVED TO BE CORRECT AND RELIABLE. HOWEVER, NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THESE DATA, AND NONE IS MADE AS TO THE MARKETABILITY OF THE MATERIAL OR ITS FITNESS FOR ANY PURPOSE. THE CONSUMER ACCEPTS THE RESPONSIBILITY OF AND THE CONDITIONS FOR LIABILITY OF USE OF THE PRODUCT.