



# **TSE-EZNATE® 1100**

## **Aliphatic polyisocyanate (low-viscosity trimer)**

### **Product Description**

TSE-EZNATE® 1100 is used as the hardener component for lightfast polyurethane, polyurea or polyaspartic coating systems.

### **Specification Properties**

<b>Property</b>	<b>Value</b>
Viscosity at 25°C, mPas	900-1500 cps
NCO content	23 ± 0.5 %
Color Value	≤ 40
Monomeric HDI	≤ 0.25%

### **Storage**

Store TSE-EZNATE® 1100 in tightly-closed containers, protected from contamination, moisture and foreign substances, which can adversely affect processing. Any opened packages should be blanketed using dry nitrogen and resealed tightly so as to keep moisture from entering the sealed container. TSE-EZNATE® 1100 will react with water to form ureas and CO<sub>2</sub> gas, which may cause sealed containers to expand and rupture. For maximum storage life, sealed containers should be stored between 60°F and 95°F. Shelf life is 12 months when stored this way.

### **Standard Package**

Components are supplied in 5-gallon pails (40 Lbs. net) and 55-gallon drums (450 Lbs. net).

THE INFORMATION HEREIN IS BELIEVED TO BE CORRECT AND RELIABLE. HOWEVER, NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THESE DATA, AND NONE IS MADE AS TO THE MARKETABILITY OF THE MATERIAL OR ITS FITNESS FOR ANY PURPOSE. THE CONSUMER ACCEPTS THE RESPONSIBILITY OF AND THE CONDITIONS FOR LIABILITY OF USE OF THE PRODUCT.

## **Safety and Handling**

Refer to the Safety Data Sheet (SDS) before handling TSE-EZNATE®1100. When utilizing this material, proper protective equipment must be worn. It is the responsibility of the operator to completely read and understand the SDS for each component before handling them.

If for any reason you are not clear on the proper safety and handling procedures, please contact your supervisor or a TSE representative for additional information.

## **Product Support:**

TSE Industries, Inc.  
PU Elastomers Division  
5180 113<sup>th</sup> Avenue North  
Clearwater, FL 33760 USA

1-727-573-7676 or 1-800-237-7634

[www.tse-industries.com](http://www.tse-industries.com)

THE INFORMATION HEREIN IS BELIEVED TO BE CORRECT AND RELIABLE. HOWEVER, NO WARRANTY IS EXPRESSED OR IMPLIED REGARDING THE ACCURACY OF THESE DATA, AND NONE IS MADE AS TO THE MARKETABILITY OF THE MATERIAL OR ITS FITNESS FOR ANY PURPOSE. THE CONSUMER ACCEPTS THE RESPONSIBILITY OF AND THE CONDITIONS FOR LIABILITY OF USE OF THE PRODUCT.